

JM PVC SD PLUS — 60 N

Polyester-Reinforced Thermoplastic Polyvinyl Chloride Membrane


Meets the requirements of ASTM D 4434, Type III

Features and Components

Non-wicking Reinforced Polyester Scrim: Our fully integrated manufacturing process adds tensile strength and toughness. Edge sealant is not a requirement for cut edges.

Excellent Chemical Resistance: JM PVC is inherently resistant to oils, air conditioning coolants, fuels and grease.

Energy Savings: The white membranes provide exceptional reflectivity and emissivity for energy savings.





Color

White, Grey

*Grey, only available in 120" x 100' - call for availability, lead-time, and minimums

JM Membranes are designed with a cap, core, and bottom in order to utilize recycled content. The cap, or top-side is produced with non-recycled content, and should always be install facing up. The cap is identified by the lap line and production code.

System Compatibility This product may be used as a component in the following systems. Please reference product application for specific installation methods and information.

Ρl	BUR APP			SBS				1	Ρl	T	20	P	VC		EPDM		
ulti-	HA	CA	CA	HW	HA	CA	HW	SA	·	ngle	MF	FA	MF	FA	MF	FA	BA
Ē	Do not use with Multi-Ply systems					i	5 Compatible with the selected Single Ply systems above				,						

Key: HA = Hot Applied CA = Cold Applied HW = Heat Weldable SA = Self Adhered MF = Mechanically Fastened FA = Fully Adhered BA = Ballasted

Energy and the Environment Standard Reflectivity Emissivity White Initial 0.86 0.86 **CRRC®** 0.70 0.82 3 Yr. Aged White CA Title 24 Pass 0.86 0.86 White 0.86 ENERGY Initial 0.86 **STAR®** 0.70 3 Yr. Aged **LEED**[®] White Initial 108 (SRI) 3 Yr. Aged 84 Post-consumer 0% Recycled

Content Post-industrial 0% - 10% The LEED® Solar Reflectance Index (SRI) is calculated per ASTM E1980.

Peak Advantage® Guarantee Information

Product Thickness	Terms
60 mil	5, 10, 15 or 20 yr NDL

Guarantee terms are for mechanically fastened and fully adhered systems. Mixed-membrane jobs - JM PVC SD Plus and JM PVC (KEE) - will not be eligible for a JM Peak Advantage Guarantee

Codes and Approvals



Installation/Application



Hot Air Weld

Fastened Refer to JM PVC application guides and detail drawings

for instructions.

Packaging and Dimensions

Sizes	Coverage			
5' x 100' (1.52 m x 30.48 m)	500 ft² (46.33 m²)			
10' x 100' (3.05 m x 30.48 m)	1000 ft² (92.96 m²)			
Widths	5'	10'		
Rolls per Pallet	9	9		
Pallet Weight - Ib (kg)	1800 (816.5)	3865 (1753.1)		
Pallets per Truck*	17	8		
Producing Locations	id Pawtucket, RI			

*Assumes 48' flatbed truck.

JM PVC accessories are formulated to be compatible with JM PVC SD Plus and JM PVC.



JM PVC SD PLUS — 60 MIL

Polyester-Reinforced Thermoplastic Polyvinyl Chloride Membrane

Meets the requirements of ASTM D 4434, Type III

Manufactured Physical Properties

Physic	cal Properties	ASTM Test Method	ASTM Requirements	60 mil Result	
	Breaking Strength, min, Ibf/in (N)	D 751	200 (890)	240 (1,068)	
	Elongation at Break, min, %	D 751	15	15	
Strength	Tearing Strength, min, lbf (N)	D 751	45 (200)	45 (200)	
Stre	Seam Strength, min, % of breaking strength	D 751	75	80	
	Static Puncture Resistance lbf (kg)	D 5602	Pass @ 33 (15)	Pass	
	Dynamic Puncture Resistance J	D 5635	Pass @ 20	Pass	
	Thickness, min, in.	D 751	+/- 10% from Nominal	0.060 Nominal	
Longevity	Thickness Over Scrim, min, in.	D 7635	0.016	0.023	
Long	Change in Weight After Immersion in Water, max, %	D 570 modified	3.0	3.0	
	Low Temperature Bend, °F	D 2136	No cracks @ -40° F	Pass	
	Properties after Heat Aging, min	D 3045	56 days @ 176° F		
ged ance	Breaking Strength, %	D 751	90	>90	
Heat Aged Performance	Elongation, %	D 751	90	>90	
H	Linear Dimensional Change, max, % after 6 hrs @ 176° F	D 1204	0.5	<0.5	
0	Accelerated Weathering, min	G 151 & G 154	5,000 hrs		
Weather	Cracking (@7x magnification)	G 154	No cracks	Pass	
Weather Performance	Discoloration (by observation)	G 154	Negligible	Negligible	
ď	Crazing (@7x Magnification)	G 154	No crazing	Pass	